FERROXCUBE

DATA SHEET

EC35 EC cores and accessories

Supersedes data of September 2004

2008 Sep 01




EC35

CORE SETS

Effective core parameters

SYMBOL	PARAMETER	VALUE	UNIT
Σ(I/A)	core factor (C1)	0.918	mm ⁻¹
V _e	effective volume	6530	mm ³
l _e	effective length	77.4	mm
A _e	effective area	84.3	mm ²
A _{min}	minimum area	71	mm ²
m	mass of core half	≈ 19	g



Core halves

 A_{L} measured in combination with an non-gapped core half, unless stated otherwise.

GRADE	A _L (nH)	μ _e	TOTAL AIR GAP (μm)	TYPE NUMBER
3C81 sup	100 ± 3% ⁽¹⁾	≈ 73	≈ 1470	EC35-3C81-E100
	$160 \pm 3\%^{(1)}$	≈ 117	≈ 820	EC35-3C81-E160
	$250\pm3\%$	≈ 184	≈ 470	EC35-3C81-A250
	315 ± 5%	≈ 231	≈ 350	EC35-3C81-A315
	$400\pm10\%$	≈ 290	≈ 260	EC35-3C81-A400
	≥ 2250	≥ 1640	≈ 0	EC35-3C81
3C90 sup	$100 \pm 3\%^{(1)}$	≈ 73	≈ 1470	EC35-3C90-E100
	$160 \pm 3\%^{(1)}$	≈ 117	≈ 820	EC35-3C90-E160
	250 ± 3%	≈ 184	≈ 470	EC35-3C90-A250
	315 ± 5%	≈ 231	≈ 350	EC35-3C90-A315
	400 ±10%	≈ 290	≈ 260	EC35-3C90-A400
	2100 ±25%	≈ 1530	≈ 0	EC35-3C90

Note

1. Measured in combination with an equal gapped core half (symmetrical air gap).

Properties of core sets under power conditions

	B (mT) at	CORE LOSS (W) at		
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 25 kHz; B = 200 mT; T = 100 °C	f = 100 kHz; B = 100 mT; T = 100 °C	
3C81	≥320	≤ 1.40	-	
3C90	≥320	≤ 0.79	≤ 0.83	


EC cores and accessories

EC35

COIL FORMERS

General data 8-slots EC35 coil former for insertable pins

PARAMETER	SPECIFICATION
Coil former material	polyamide (PA6.6), glass-reinforced, flame retardant in accordance with "UL 94V-0"; UL file number E44716(M)
Maximum operating temperature	130 °C, "IEC 60085", class B



Winding data and area product for 8-slots EC35 coil former for insertable pins

Coil formers with inserted pins are available on request.


NUMBER OF SECTIONS	MINIMUM WINDING AREA (mm²)	NOMINAL WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	AREA PRODUCT Ae x Aw (mm ⁴)	TYPE NUMBER
1	97.1	21.5	53.1	8190	CP-EC35-1S


EC35


MOUNTING PARTS


General data and ordering information


ITEM	REMARKS	MOUNT	FIGURE	TYPE NUMBER
Insertable pins	solderability: "IEC 68-2-20", Part 2,	general	3	PIN-EC
	Test Ta, method 1; material: copper-zinc alloy (CuZn), tin (Sn) plated	horizontal	4	PIN/H-EC
Base plate 2 holes	aluminium		5	BPL2-EC35
Base plate 4 holes	plate 4 holes aluminium		6	BPL4-EC35
Clamp	copper-zinc alloy (CuZn)		7	CLM/U-EC35











2008 Sep 01

601

EC cores and accessories

EC35

DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in	des	These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support	sup	These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.