
FERROXCUBE



Supersedes data of September 2004

2008 Sep 01




PT23/18 (2318TS)

CORE SETS

Effective core parameters

SYMBOL	PARAMETER	VALUE	UNIT
Σ(I/A)	core factor (C1)	0.670	mm ⁻¹
Ve	effective volume	2590	mm ³
l _e	effective length	41.6	mm
A _e	effective area	62.2	mm ²
A _{min}	minimum area	53.6	mm ²
m	mass of set	≈ 14	g



Core sets for general purpose transformers and power applications

Clamping force for A_L measurements, 30 ± 10 N.

GRADE	A _L (nH)	μ _e	AIR GAP (μm)	TYPE NUMBER
3C81 sup	160 ±3%	≈ 85	≈ 620	PT23/18-3C81-A160
	250 ±3%	≈ 133	≈ 360	PT23/18-3C81-A250
	315 ±3%	≈ 168	≈ 270	PT23/18-3C81-A315
	400 ±3%	≈ 213	≈ 200	PT23/18-3C81-A400
	630 ±5%	≈ 335	≈ 120	PT23/18-3C81-A630
	4100 ±25%	≈ 2180	≈ 0	PT23/18-3C81
3C91 sup	4100 ±25%	≈ 2180	≈ 0	PT23/18-3C91
3F3 sup	160 ±3%	≈ 85	≈ 620	PT23/18-3F3-A160
	250 ±3%	≈ 133	≈ 360	PT23/18-3F3-A250
	315 ±3%	≈ 168	≈ 270	PT23/18-3F3-A315
	400 ±3%	≈ 213	≈ 200	PT23/18-3F3-A400
	630 ±5%	≈ 335	≈ 120	PT23/18-3F3-A630
	2750 ±25%	≈ 1460	≈ 0	PT23/18-3F3

Core sets of high permeability grades

Clamping force for A_L measurements, 30 ± 10 N.

GR	ADE	A _L (nH)	μ _e	AIR GAP (μm)	TYPE NUMBER
3E27	sup	6400 ±25%	≈ 3410	≈ 0	PT23/18-3E27

Properties of core sets under power conditions

	B (mT) at CORE LOSS (W) a			OSS (W) at) at	
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 25 kHz; B = 200 mT; T = 100 °C	f = 100 kHz; B = 100 mT; T = 100 °C	f = 100 kHz; B = 200 mT; T = 100 °C	f = 400 kHz; B = 50 mT; T = 100 °C	
3C81	≥320	≤0.6	-	-	-	
3C91	≥320	-	$\leq 0.13^{(1)}$	≤ 1.0 ⁽¹⁾	-	
3F3	≥315	—	≤ 0.29	—	≤ 0.49	


Note

1. Measured at 60 °C.

COIL FORMER

General data 10-pins PT23/18 coil former

PARAMETER	SPECIFICATION
Coil former material	polyamide (PA), glass-reinforced, flame retardant in accordance with <i>"UL 94V-0"</i> ; UL file number E41938(M)
Pin material	copper-tin alloy (CuSn), tin (Sn) plated
Maximum operating temperature	130 °C, <i>"IEC 60085</i> ", class B
Resistance to soldering heat	"IEC 60068-2-20", Part 2, Test Tb, method 1B, 350 °C, 3.5 s
Solderability	"IEC 60068-2-20", Part 2, Test Ta, method 1



Winding data and area product for 10-pins PT23/18 coil former

NUMBER OF SECTIONS	MINIMUM WINDING AREA (mm ²)	NOMINAL WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	AREA PRODUCT Ae x Aw (mm ⁴)	TYPE NUMBER
1	36.0	11.8	45.2	2240	CPV-PT23/18-1S-10P

DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in	des	These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support	sup	These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.